

Both sides wide seal range heat sealable, one side treated coextruded BOPP film.

Properties

- · Strong seals
- · Excellent hot tack
- · High heat seal strength
- · High coefficient of friction

Applications

Designed for single web overwrap and for lamination to itself and other substrates where low slip is required.

PROPERTIES	TEST CONDITIONS		UNITS	TYPICAL VALUES				
THICKNESS			μ	17	18	20	25	30
THICKNESS			Gauge	68	72	80	100	120
THICKNESS TOLERANCE			%	5				
UNIT WEIGHT	ASTM D 2673		g / m²	15.4	16.3	18.1	22.6	27.2
YIELD	ASTM D 2673		m² / kg	64.9	61.3	55.2	44.2	36.7
HAZE	ASTM D 1003		%	< 2.5				
GLOSS	ASTM D 2457		%	85 ± 5				
OPTICAL DENSITY	MACBETH							
COEFFICIENT OF FRICTION	ASTM D 1894	B/B*		< 0.40				
		B/M*		< 0.30				
TENSILE STRENGTH	ASTM D 882	MD	N/mm²	120 ± 20				
		TD		270 ± 50				
ELONGATION AT BREAK	ASTM D 882	MD	%	190 ± 40				
		TD		45 ± 10				
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec		°C	110 - 145				
SEAL STRENGTH	130 ℃ / 3 Bar / 0.5 Sec		N/15mm	> 2.5				
WVTR	ASTM F 1249 38℃ / 90% RH		g/m²/day	7.	.5	6.0	5.0	4.5
TREATMENT LEVEL	ASTM D 2578		dyne/cm	≥ 38				
HEAT SHRINKAGE	130℃ / 7 mln	MD	%	≤ 5.0				
		TD		≤ 3.0				

^{*}B/B: Nontreated side to nontreated side

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB Izmir-TURKIYE

Phone: +90 232 3767970 Fax: +90 232 3767730 E-Mail: polibak@polibak.com.tr www.polibak.com.tr

Reference No: 2013/10/03

^{*}All COF values are dynamic results

^{*}B/M: Nontreated side to metal