

Both sides treated white pigmented BOPP film.

## Properties

- High protection against light for food packaging
- Whiteness eliminates need of white ink, therefore it reduces problems of residual solvents from printing

## Applications

White film for surface print and also lamination, cold seal and release lacquer applications.

PROPERTIES	TEST CONDITIONS	UNITS	TYPICAL VALUES		
THICKNESS	.....	μ	18	20	30
		Gauge	72	80	120
THICKNESS TOLERANCE	.....	%	5		
UNIT WEIGHT	ASTM D 2673	g / m <sup>2</sup>	17.3 ± 1.2	19.2 ± 1.3	28.8 ± 2.0
YIELD	ASTM D 2673	m <sup>2</sup> / kg	57.8 ± 4	52.1 ± 3.5	34.72 ± 2.5
HAZE	ASTM D 1003	%	.....		
GLOSS	ASTM D 2457	%	50 ± 5		
OPTICAL DENSITY	MACBETH	.....	0.38 ± 0.02		0.42 ± 0.02
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*	.....		
		B/M*			
TENSILE STRENGTH	ASTM D 882	MD	120 ± 20		
		TD	270 ± 50		
ELONGATION AT BREAK	ASTM D 882	MD	190 ± 40		
		TD	45 ± 10		
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec	°C	.....		
SEAL STRENGTH	130°C / 3 Bar / 0.5 Sec	N / 15 mm	.....		
WVTR	ASTM F 1249 38°C / 90% RH	g / m <sup>2</sup> / day	7.0		
TREATMENT LEVEL	ASTM D 2578	dyne / cm	> 38 (both)		
HEAT SHRINKAGE	130°C / 7 mIn	MD	< 5.0		
		TD	< 3.0		

\*B/B : Nontreated side to nontreated side

\*All COF values are dynamic results

\*B/M : Nontreated side to metal

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB İzmir-TURKIYE

Phone : +90 232 3767970 Fax : +90 232 3767730

E-Mail : polibak@polibak.com.tr www.polibak.com.tr

Reference No : 2013/12/04